

**AMENDMENTS TO THE CLAIMS**

**This listing of claims will replace all prior versions and listings of claims in the application:**

**LISTING OF CLAIMS:**

1. (original): A fluoropolymer containing acid/acid salt groups and having  $-\text{CF}_2\text{H}$  groups at polymer chain terminals,

wherein said acid/acid salt groups are sulfonic acid groups,  $-\text{SO}_2\text{NR}^1\text{R}^2$ ,  $-\text{SO}_3\text{NR}^3\text{R}^4\text{R}^5\text{R}^6$ ,  $-\text{SO}_3\text{M}^1_{1/\text{L}}$ , phosphoric acid groups,  $-\text{PO}_3(\text{NR}^7\text{R}^8\text{R}^9\text{R}^{10})_2$  and/or  $-\text{PO}_3\text{M}^2_{2/\text{L}}$ ; in the formula  $\text{R}^1$  represents H or  $\text{M}^6_{1/\text{L}}$ ,  $\text{R}^2$  represents H,  $\text{M}^7_{1/\text{L}}$ , an alkyl group or a sulfonyl-containing group,  $\text{R}^3$ ,  $\text{R}^4$ ,  $\text{R}^5$ ,  $\text{R}^6$ ,  $\text{R}^7$ ,  $\text{R}^8$ ,  $\text{R}^9$  and  $\text{R}^{10}$  are the same or different and each represents H or an alkyl group containing 1 to 4 carbon atoms,  $\text{M}^1$ ,  $\text{M}^2$ ,  $\text{M}^6$  and  $\text{M}^7$  are the same or different and each represents a metal having a valence of L, said metal having a valence of L being a metal belonging to the group 1, 2, 4, 8, 11, 12 or 13 of the long-form periodic table.

2. (original): The fluoropolymer according to Claim 1,


said fluoropolymer being one obtained by subjecting a fluoropolymer precursor containing acid/acid salt groups and having  $-\text{CF}_2\text{COOX}$  groups at polymer chain terminals, in the formula X represents H,  $\text{NR}^{11}\text{R}^{12}\text{R}^{13}\text{R}^{14}$  or  $\text{M}^4_{1/\text{L}}$ ;  $\text{R}^{11}$ ,  $\text{R}^{12}$ ,  $\text{R}^{13}$  and  $\text{R}^{14}$  are the same or different and each represents H or an alkyl group containing 1 to 4 carbon atoms and  $\text{M}^4$  represents a metal having a valence of L, said metal having a valence of L being as defined

above, to heat treatment by which said  $-\text{CF}_2\text{COOX}$  groups can be converted to  $-\text{CF}_2\text{H}$  groups, X being as defined above.

3. (currently amended): The fluoropolymer according to Claim 1 ~~or 2~~, wherein said acid/acid salt groups are sulfonic acid groups,  $-\text{SO}_3\text{NR}^3\text{R}^4\text{R}^5\text{R}^6$  and/or  $-\text{SO}_3\text{M}^1_{1/L}$ ,  $\text{R}^3$ ,  $\text{R}^4$ ,  $\text{R}^5$ ,  $\text{R}^6$  and  $\text{M}^1$  being as defined above.

4. (currently amended): The method of producing the fluoropolymer according to ~~any one of Claims 1 to 3~~ Claim 1, by subjecting a fluoropolymer precursor containing acid/acid salt groups and having  $-\text{CF}_2\text{COOX}$  groups at polymer chain terminals, in the formula X represents H,  $\text{NR}^{11}\text{R}^{12}\text{R}^{13}\text{R}^{14}$  or  $\text{M}^4_{1/L}$ ;  $\text{R}^{11}$ ,  $\text{R}^{12}$ ,  $\text{R}^{13}$  and  $\text{R}^{14}$  are the same or different and each represents H or an alkyl group containing 1 to 4 carbon atoms and  $\text{M}^4$  represents a metal having a valence of L, said metal having a valence of L being a metal belonging to the group 1, 2, 4, 8, 11, 12 or 13 of the long-form periodic table, to heat treatment for the conversion of said  $-\text{CF}_2\text{COOX}$  groups to  $-\text{CF}_2\text{H}$  groups, X being as defined above,

wherein said fluoropolymer precursor is one obtained by polymerizing a perhalovinyl ether derivative represented by the general formula (I):



wherein  $\text{Y}^1$  represents F, Cl or a perfluoroalkyl group, n represents an integer of 0 to 3, the n atoms/groups of  $\text{Y}^1$  are the same or different,  $\text{Y}^2$  represents F or Cl, m represents an integer of 1 to 5, the m atoms of  $\text{Y}^2$  are the same or different and Z represents F, Cl, Br, I,  $-\text{OM}^5_{1/L}$  or

$-\text{ONR}^{15}\text{R}^{16}\text{R}^{17}\text{R}^{18}$ ;  $\text{M}^5$  represents a metal having a valence of L and the metal having a valence of L is as defined above, and  $\text{R}^{15}$ ,  $\text{R}^{16}$ ,  $\text{R}^{17}$  and  $\text{R}^{18}$  are the same or different and each represents H or an alkyl group containing 1 to 4 carbon atoms,

when the group  $-\text{SO}_2\text{Z}$  in the general formula (I) is not said acid/acid salt group but is a group convertible to such acid/acid salt group, said fluoropolymer precursor is one subjected to a conversion treatment, after the above-mentioned polymerization, for the conversion of said group  $-\text{SO}_2\text{Z}$  to the above-mentioned acid/acid salt group, and

said heat treatment comprises heating said fluoropolymer precursor at 120 to 400°C.

5. (original): The method of producing a fluoropolymer according to Claim 4, wherein the heat treatment comprises heating the fluoropolymer precursor at 120 to 200°C in the presence of water or an organic solvent having compatibility with water.

6. (original): The method of producing a fluoropolymer according to Claim 5, wherein the organic solvent having compatibility with water is an organic liquid having a boiling point exceeding 100°C but not exceeding 300°C.

7. (currently amended): The method of producing a fluoropolymer according to ~~any one of Claims 4 to 6~~Claim 4,

wherein the fluoropolymer precursor is an at least binary copolymer obtained by polymerizing the perhalovinyl ether derivative and a monomer copolymerizable with said perhalovinyl ether derivative.

8. (currently amended): The method of producing a fluoropolymer according to ~~any one of Claims 4 to 7~~Claim 4,

wherein  $Y^2$  is F, n is 0 or 1 and m is 2 or 3.

9. (currently amended): The method of producing a fluoropolymer according to ~~any one of Claims 4 to 8~~Claim 4,

wherein the fluoropolymer precursor constitutes a powder, dispersion, solution or membrane-shaped molding.

10. (original): The method of producing a fluoropolymer according to Claim 9, wherein the fluoropolymer precursor constitutes a membrane-shaped molding.

11. (currently amended): An electrolyte membrane comprising the fluoropolymer according to ~~any one of Claims 1 to 3~~Claim 1.

12. (currently amended): An immobilized active substance material comprising the fluoropolymer according to ~~any one of Claims 1 to 3~~Claim 1 and an active substance.

13. (original): The immobilized active substance material according to Claim 12, wherein the active substance is a catalyst.

14. (original): The immobilized active substance material according to Claim 13,

Preliminary Amendment  
Based on PCT/JP2004/018885

wherein the catalyst is a platinum-containing metal.

15. (currently amended): A membrane-electrode assembly comprising the immobilized active substance material according to Claim 13 ~~or~~ 14.

16. (original): A solid polymer electrolyte fuel cell comprising the membrane-electrode assembly according to Claim 15.

17. (original): A solid polymer electrolyte fuel cell comprising the electrolyte membrane according to Claim 11.